

CLAIM AMENDMENTS

1. (Currently Amended) A polybenzazole article superior in light resistance, which comprises a polybenzazole and a light-resisting agent that allows for a regular reflectance of the article of not more than 30% in not less than 30% of the wavelength region of from 450 nm to 700 nm, wherein the light-resisting agent is at least one member selected from the group consisting of ~~aniline, o-phenylenediamine~~, *m*-phenylenediamine, *p*-phenylenediamine, *o*-aminophenol, ~~*m*-aminophenol, *p*-aminophenol~~, 2-amino-4-nitrophenol, 2-aminophenol-4-sulfonamide, and 1,8-diaminonaphthalene.

2. (Original) The polybenzazole article of claim 1, wherein the light-resisting agent allows for a regular reflectance of the article of not more than 20% in not less than 10% of the wavelength region of from 450 nm to 700 nm.

3. (Original) The polybenzazole article of claim 1, which has a strength of not less than 35 g/d.

4. (Canceled)

5. (Canceled)

6. (Original) The polybenzazole article of claim 1, wherein the light-resisting agent is contained in a proportion of 0.01 to 20% by weight of the article.

7. (Canceled)

8. (Canceled)

9. (New) The polybenzazole article of claim 1, wherein the light-resisting agent comprises *m*-phenylenediamine and *p*-phenylenediamine in a weight ratio of about 1:1.

10. (New) The polybenzazole article of claim 1, wherein the light-resisting agent comprises *o*-aminophenol and *p*-phenylenediamine in a weight ratio of about 1:1.

In re Appln. of Kodama et al.
Application No. 09/502,834

11. (New) The polybenzazole article of claim 1, wherein the light-resisting agent comprises 2-amino-4-nitrophenol and *p*-phenylenediamine in a weight ratio of about 1:1.